



Technical Data

STYROFOAM™ LBH-X

Properties	Standard	Unit	STYROFOAM™ LBH-X	CE-Code
Cell content			HFC	
Density (typical value)	EN 1602	kg/m ³	33	-
Thermal conductivity declared (λ_D)	EN 13164	W/(m.K)	0,033	λ_D
Compressive stress or compressive strength @ 10% deformation ¹⁾	EN 826	kPa	300	CS(10Y)
Tensile strength ¹⁾	EN 1607	kPa	500	TR
Shear strength	EN 12090	kPa	250	SS
Moduli (typical values)				
E-Modulus ¹⁾	EN 826	MPa	12 (≤ 30 mm) 15 (31-80mm) 20 (> 80 mm)	-
Tensile modulus ¹⁾	EN 1607	MPa	24 (≥ 50 mm)	-
Shear modulus G	EN 12090	MPa	10	-
Water vapour diffusion resistance factor μ (tabulated value)	EN 12086	-	150	MU
Long term water absorption by total immersion	EN 12087	Class	1,5	WL(T)
Dimensional stability under specified temperature (70°C) and humidity conditions (90%rh)	EN 1604	%	5	DS(70,90)
Capillarity	-	%	0	-
Coefficient of linear thermal expansion (typical value)	-	mm/(m.K)	0,07	-
Reaction to fire Euroclass	EN 13501-1	-	E	-
Temperature limits	-	°C	-50/+75	-
Dimensions ²⁾				
Thickness	EN 823	mm	20-200	-
Width	EN 822	mm	600/1200	-
Length	EN 822	mm	2500/3000	-
Tolerances				
Thickness	EN 823	mm	-/+0,5	T
Width	EN 822	mm	<700mm: -0/+3 ≥ 700 mm: -0/+5	-
Length	EN 822	mm	-0/+10	-
Edge Profile	-	-	butt edge	-
Surface Finish	-	-	planned/grooved	-

Designation Code: XPS - EN 13164 - T3 - CS(10Y)300 - DS(70,90) - WL(T)1,5 - TR400 - SS250 - MU150

1) Measured in thickness direction.

2) Products with special dimensions or closer tolerances are available upon request.

1 N/mm² = 10³ kPa; 1 kPa = 10⁻³ Mpa.

January 2014 - This document supersedes all previous versions and editions

Note:

The information and data contained in this technical data sheet do not represent exact sales specifications. The features of the products mentioned may vary. The information contained in this document has been provided in good faith, however it does not imply any liability, guarantee or assurance of product performance. It is the purchaser's responsibility to determine whether these Dow products are suitable for the application desired and to ensure that the site of work and method of application conform with current legislation. No license is hereby granted for the use of patents or other industrial or intellectual property rights. If Dow products are purchased, we advise following the most up-to-date suggestions and recommendations.

Dow Chemical Company Limited

Dow Building Solutions

Diamond House, Lotus Park
Kingsbury Crescent, Staines, TW18 3AG

Tel: 020 3139 4000

Fax: 020 3139 401

Internet: www.dowcorecomposites.com

www.dowdop.com

291-71525-0114